

Docket No. 740756-2659
Application No. 10/678,139
Page 2

Amendments to the Claims:

This listing of claims will replace all prior versions, and listings, of claims in the application:

Listing of Claims:

1-6. (Cancelled).

7. (Currently Amended) A method of manufacturing a semiconductor device comprising:

providing an amorphous semiconductor film with a metal element for promoting crystallization of said semiconductor film;

heating said amorphous semiconductor film to crystallize said amorphous semiconductor film;

forming a metal element diffusion film comprising a semiconductor ~~directly on over~~ the crystallized semiconductor film, said forming of the metal element diffusion film increasing a defect density of the metal element diffusion film;

diffusing the metal element from the crystallized semiconductor film into the metal element diffusion film; and

removing the metal element diffusion film after the step of diffusing the metal element.

8. (Previously Presented) The method of claim 7 wherein said metal element diffusion film is an amorphous silicon film.

9. (Previously Presented) The method of claim 7 wherein said metal element diffusion film is a polycrystalline silicon film.

10. (Previously Presented) The method of claim 7 wherein said metal element diffusion film is an amorphous $\text{Si}_x\text{Ge}_{1-x}$ film where $0 < x < 1$.

W648126.1

Best Available Copy

Docket No. 740756-2659
Application No. 10/678,139
Page 3

11. (Previously Presented) The method of claim 7 wherein said metal element is at least one of Fe, Co, Ni, Ru, Rh, Pd, Os, Ir, Pt, Cu and Au.
12. (Currently Amended) A method of manufacturing a semiconductor device comprising:
- providing a selected portion of an amorphous semiconductor film with a metal element for promoting crystallization of said semiconductor film;
 - heating said amorphous semiconductor film to crystallize said amorphous semiconductor film wherein the crystallization proceeds from said selected portion laterally;
 - forming a metal element diffusion film comprising a semiconductor ~~directly on over~~ the crystallized semiconductor film, said forming of the metal element diffusion film increasing a defect density of the metal element diffusion film;
 - diffusing the metal element from the crystallized semiconductor film into the metal element diffusion film; and
 - removing the metal element diffusion film after the step of diffusing the metal element.
13. (Previously Presented) The method of claim 12 wherein said metal element diffusion film is an amorphous silicon film.
14. (Previously Presented) The method of claim 13 wherein said metal element diffusion film is a polycrystalline silicon film.
15. (Previously Presented) The method of claim 13 wherein said metal element diffusion film is an amorphous $\text{Si}_x\text{Ge}_{1-x}$ film where $0 < x < 1$.
16. (Previously Presented) The method of claim 15 wherein said metal element is at least one of Fe, Co, Ni, Ru, Rh, Pd, Os, Ir, Pt, Cu and Au.

W648126.1

Docket No. 740756-2659
Application No. 10/678,139

Page 4

17. (Previously Presented) A method of manufacturing a semiconductor device comprising:
- providing an amorphous semiconductor film with a metal element for promoting crystallization of said semiconductor film;
 - heating said amorphous semiconductor film to crystallize said amorphous semiconductor film;
 - forming a metal element diffusion film comprising a semiconductor ~~directly on over~~ the crystallized semiconductor film, said forming of the metal element diffusion film increasing a defect density of the metal element diffusion film;
 - diffusing the metal element from the crystallized semiconductor film into the metal element diffusion film by irradiating the crystallized semiconductor film with laser; and
 - removing the metal element diffusion film after the step of diffusing the metal element.
18. (Previously Presented) The method of claim 17 wherein said metal element diffusion film is an amorphous silicon film.
19. (Previously Presented) The method of claim 17 wherein said metal element diffusion film is a polycrystalline silicon film.
20. (Previously Presented) The method of claim 17 wherein said metal element diffusion film is an amorphous $\text{Si}_x\text{Ge}_{1-x}$ film where $0 < x < 1$.
21. (Previously Presented) The method of claim 17 wherein said metal element is at least one of Fe, Co, Ni, Ru, Rh, Pd, Os, Ir, Pt, Cu and Au.
22. (Currently Amended) A method of manufacturing a semiconductor device comprising:
- providing an amorphous semiconductor film with a metal element for promoting crystallization of said semiconductor film;

W645126.1

Docket No. 740756-2659
Application No. 10/678,139
Page 5

heating said amorphous semiconductor film to crystallize said amorphous semiconductor film;

forming an etching stopper film on the crystallized semiconductor film;

forming a metal element diffusion film comprising a semiconductor over the crystallized semiconductor film with the etching stopper film interposed therebetween, said forming of the metal element diffusion film increasing a defect density of the metal element diffusion film;

diffusing the metal element from the crystallized semiconductor film into the metal element diffusion film by irradiating the crystallized semiconductor film with laser; and

removing the metal element diffusion film after the step of diffusing the metal element.

23. (Previously Presented) The method of claim 22 wherein said metal element diffusion film is an amorphous silicon film.

24. (Previously Presented) The method of claim 22 wherein said metal element diffusion film is a polycrystalline silicon film.

25. (Previously Presented) The method of claim 22 wherein said metal element diffusion film is an amorphous $\text{Si}_x\text{Ge}_{1-x}$ film where $0 < x < 1$.

26. (Previously Presented) The method of claim 22 wherein said metal element is at least one of Fe, Co, Ni, Ru, Rh, Pd, Os, Ir, Pt, Cu and Au.

27. (Previously Presented) The method of claim 22 wherein said etching stopper film comprises silicon nitride.

28. (Previously Presented) The method of claim 22 wherein said etching stopper film comprises silicon oxide.

W648126.1

Docket No. 740756-2659
Application No. 10/678,139
Page 6

29. (New) The method according to claim 7 wherein said metal diffusion film is formed on said crystallized semiconductor film.

W648126.1

**This Page is Inserted by IFW Indexing and Scanning
Operations and is not part of the Official Record**

BEST AVAILABLE IMAGES

Defective images within this document are accurate representations of the original documents submitted by the applicant.

Defects in the images include but are not limited to the items checked:

- ☐ **BLACK BORDERS**
- ☐ **IMAGE CUT OFF AT TOP, BOTTOM OR SIDES**
- ☐ **FADED TEXT OR DRAWING**
- ☐ **BLURRED OR ILLEGIBLE TEXT OR DRAWING**
- ☐ **SKEWED/SLANTED IMAGES**
- ☐ **COLOR OR BLACK AND WHITE PHOTOGRAPHS**
- ☐ **GRAY SCALE DOCUMENTS**
- ☒ **LINES OR MARKS ON ORIGINAL DOCUMENT**
- ☐ **REFERENCE(S) OR EXHIBIT(S) SUBMITTED ARE POOR QUALITY**
- ☐ **OTHER:** _____

IMAGES ARE BEST AVAILABLE COPY.

As rescanning these documents will not correct the image problems checked, please do not report these problems to the IFW Image Problem Mailbox.